



Comparison Data Sheet

Ultraflon™ MP-80/92 PTFE vs. Dyneon™ TF 9205*

Property	Unit of Measure	Test Method	MP-80/92	TF 9205*
Appearance		Visual	White	White
Melt Point Temperature	°C	DSC	325 ± 5.0	325
Particle Size (D50)	Microns	Laser Diffraction	8.0 ± 1.5	8.0

All information and statements given are, to the best of our knowledge, true and accurate, but are presented without warranty or representation, expressed or implied. The user should assume responsibility for use and safety based on their appraisal. All Ultraflon products should be tested prior to accepting as a replacement for any product.

*Information obtained about the competitor's product was ascertained from their website and/or product brochure/data sheets. The confirmation as to the validity of this data should be addressed to the competitor. This data should be used as a barometer and only to judge the relationship to the properties of the Ultraflon product. Dyneon and TF 905 are registered trademarks of 3M or its affiliates.